
TERRAZZO























TERRAZZO

In the world of interior design, terrazzo tiles are currently at the forefront of fashion trends. Their unique speckled appearance, created by a mixture of chips and aggregates, gives a distinct and artistic look.

These tiles exude a sense of vitality. The random patterns and color combinations within terrazzo tiles bring a dynamic energy to any space.

In luxury hotels, high - end residences, and upscale office buildings, terrazzo tiles are often the choice for those who demand the best in both aesthetics and quality. They are a symbol of refined taste and a statement of luxury in any interior design scheme.







TERRAZZO

Sliptech

2 COLOURS







MIX

NOUGAT


4 SIZES



120×60cm 48''× 24''



60×60cm 24''× 24''




60×30cm 24''× 12'' 12''× 12''

30×30cm

10mm 120×60cm 48''× 24''


9mm60×60cm 24"× 24"
60×30cm 24"× 12"
30×30cm 12"× 12"








• Floor . SAVANA - SAND MATT 60X60cm - 24''× 24''



• Floor . TERRAZZO - MIX SLIPTECH 60X120cm - 48''× 24''









☑ Sliptech



TECHNICAL SPECIFICATIONS

TECHNICAL CHARACTERISTIC	STANDARD TEST METHOD	ISO STANDARD REQUIREMENT	OUR VALUES	
Length & Width	ISO 10545-2	±0.6%MAX	±0.30%Max	
Thickness	ISO 10545-2	±5.0%MAX	±5.0%Max	
Sides Straightness	ISO 10545-2	±5%MAX	±0.25%Max	
Rectangularity	ISO 10545-2	±0.5%MAX	±0.25%Max	
Flatness : a) Centre Curvature	ISO 10545-2	±0.5%MAX	±0.20%Max/Max2.0mm	
b) Edge Curvature	ISO 10545-2	$\pm 0.5\%$ MAX	±0.20%Max/Max2.0mm	
c) Warpage	ISO 10545-2	\pm 0.5%MAX	±0.20%Max/Max2.0mm	
Surface Quality	ISO 10545-2	≥95%FREE From visible defect	Comply	
Water Absorption	ISO 10545-3	≤0.5%	≤0.20%	
Breaking Strength	ISO 10545-4	≥1300N	≥1300N	
Modulus Of Rupture	ISO 10545-4	≥35N/mm² Individual ≥32N/mm²	≥35N/mm² Individual ≥32N/mm²	
Abrasion Resistance a) Deep Abrasion For Unglazed Tiles b) Surfaces Abrasion For Glazed Tiles	ISO 10545-6 ISO 10545-7	≤175mm³ Manuf.to state abrasion class, cycie and passed	≤160mm³ ≥PEI 3 (Dependent On Product Type)	
Crazing Test (glazed Tiles)	ISO 10545-11	No Sign Of Crazing	No Sign Of Crazing	
Frost Resistance	ISO 10545-12	Required	No Visible Crack	
Chemical Resistance a) low concentrations b) household chemicais and Swimming pool salts	ISO 10545-13 ISO 10545-13	Manuf. to state ≥class B	Class A Class B(For Polished Tiles) Class A Class B(For Polished Tiles)	
Stain Resistance a) for unglazed tiles b) for glazed tiles	ISO 10545-14 ISO 10545-14	Manuf. to state ≥class 3	≥Class 3 ≥Class 3	
Slip Resistance (Excluding Polished,Lappato And Satin Finishing)	AS/NZS 4586 App.A	Manuf. to state	Wet Pendulum≥P4 (Dependent On Product Type)	

PACKING SPECIFICATIONS


SERIES	SIZES	PCS/CTN	m²/CTN	KG/CTN	m²/PLT	KG/PLT	CTN/PLT
TERRAZZO	60x120/24"x48"	2	1.44	32	80.64	1792	56
	60x60/24"x24"	4	1.44	30	57.60	1200	40
	30x60/12"x24"	8	1.44	30	57.60	1200	40
	30x30/12"x12"	11	0.99	21	55.44	1176	56













SUBSTANTIAL VARIATION





Foshan Casagres International Co, Ltd. info@casagresintl.com www.casagresintl.com